


# 規 格 表

## SPECIFICATION

品名 Part No. : KA200

DATE: 05/02/2011

項 目 ITEM	單 位 UNIT	規 格 值 SPEC. VALUES	檢 驗 方 法 TEST METHOD
I.規格及容許差 Dimension &Tolerances			
1.厚度 Thickness:	mm	0.065 ± 10%	ASTM D-1000
2.紙蕊內徑 Inside Diameter of Roll:	mm	77 ± 1	ASTM D-1000
II.組成 Composition:			
1.原紙 Backing:		POLYIMIDE FILM	
厚度 Thickness:	mm	0.025	ASTM D-1000
2.粘膠 Glue:		SILICONE BASE	
III.物性與化性 Physical & Chemical Properties:			
1. 180° 剝離粘著力 180° Peel Adhesion			
對鋼板 To Steel:	kg/25mm	0.65 - 0.95	ASTM D-1000
2.剝離力 Unwind Force:	g/25mm	600 - 1300	ASTM D-1000
3.抗張強度 Tensile Strength:	kg/25mm	9 ↑	ASTM D-1000
4.伸長率 Elongation:	%	50 ↑	ASTM D-1000
5.耐熱性 Heat Resistance:	°C	200°C × 2hrs	
6.耐溶劑性 Solvent Resistance:	min	30 ↑	
7.耐燃性 Flammability:	sec	60 ↓	UL 510
8.破壞電壓 Dielectric Breakdown:	kv	5.2 ↑	
9.初期力 Tack:	14#/cm	1 - 5	PSTC-6
IV.備 註 Remark :			
UL File No. E50292, Cat No KA200, Temp Rating 200°C			
			
建議保存溫度 23°C (73°F) , 65% RH . 保存期限一年			
One Year Storage life; Suggested preservation temperature 23°C (73°F) ,65% RH .			
僅供參考不列入驗收標準 The above information is for reference only and should not be employed as inspection standard.			

四 維 精 密 材 料 股 份 有 限 公 司

SYMBIO,INC.

0903-000-003